

# PSDS LABZ Specimen Bags

\_\_\_\_\_\_

## Low Density Polyethylene

#### **DESCRIPTION**

**PETLIN LD C150Y** is a low density polyethylene resin for general purpose and thin film applications. It is produced by the state-of-the-art DSM Stamicarbon tubular process. It contains antioxidant (BHT free), slip and antiblock additives. It is intended primarily for blown film process. This product meets the United State Food and Drug Administration (US FDA) criteria for food contact use as specified in CFR 177.1520 (c) 3.1a & 3.2a and Commission Regulation (EU) No. 10/2011.

### **CHARACTERISTICS include:**

- Low gels
   High clarity and gloss
- High drawdown
   Good sealability, high slip and high antiblocking

### APPLICATIONS include:

Thin gauge film for: textile, laundry, dry cleaning, garment; crosslinked foams; zip bags.

### **RECOMMENDED GAUGES:**

15 - 60 microns

### **TYPICAL DATA:**

25 microns film

Product Properties*	Test Method	Units	Value
General Properties  Melt Flow Rate, I2	ASTM D 1238;B @ 190°C, 2.16kg	g/10min	5
Nominal Density	ASTM D 792	kg/m³	921
Melting Temperature	ASTM D 3417	°C	111
Vicat Softening Temperature	ASTM D 1525 (Load: 1 kg; Heating rate: 50°C/hr)	°C	94
Mechanical Properties			
Tensile Strength at Break, (MD/TD)	ASTM D 882	MPa	15/26
Elongation at Break, (MD/TD)	ASTM D 882	%	610/149
Elmendorf Tear Strength, (MD/TD)	ASTM D 1922	g/25µm	30/80
Dart Impact Strength	ASTM D 1709-15a	g	86
Other Properties			
Clarity	ASTM D 1746	%	85
Gloss (45°)	ASTM D 2457	GU	66
Haze	ASTM D 1003	%	6.5
Coefficient of Friction (COF)	ASTM D 1894	-	0.1

<sup>\*</sup>The physical properties shown are typical values obtained by averaging a number of test results and small divergence from quoted figures may occur.

# **Typical Processing Conditions**

Extrusion melt temperature of PETLIN LD C150Y in the range of from 140°C~170°C depending on the type of machine. For blown film, recommended blow-up ratio of 2 to 3:1.



# Low Density Polyethylene

#### REGULATORY

PETLIN LD C150Y complies with the following specification when processed using good extrusion practice:-

- FDA Regulation 21 CFR 177.1520 and CFR 178.2010.
- Commission Regulation (EU) No. 10/2011.
- HALAL certified.
- REACH, RoSH and SVAC.

# **AVAILABILITY**

PETLIN LD C150Y are available 25kg bags. The product type and batch number are clearly marked on each bag.

### STORAGE/HANDLING

PETLIN LD C150Y should be properly stored in well ventilated environment at a temperature of below 50°C. Prolonged or improper storage can result in deterioration of product properties. The PETRONAS Chemicals Safety Data Sheet (SDS) contains important safety information and should be viewed before using the product.

### **HEALTH & SAFETY**

PETLIN LD C150Y is not classified as a dangerous preparation. Please refer to our Safety Data Sheet (SDS) for details on various aspects of safety, recovery and disposal of the product.

### PRODUCT STEWARDSHIP

PCGB has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. Our Product Stewardship program rests with each and every individual involved with PCGB's products - from the initial concept and research, to manufacture, use, sale and disposal of each product.

### **RELATED DOCUMENTS**

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Data Sheet (SDS)

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations

### FOR MORE INFORMATION

Please contact PETRONAS Chemicals Group Berhad (PCGB), Level 15, Tower 1, PETRONAS TWIN TOWERS, KLCC, 50088 KUALA LUMPUR, MALAYSIA.

Tel: +(603) 20515000 Fax: +(603) 20511501 or visit our site www.petronaschemicals.com Sales contact person; Tel: +(603)-20511784 Email: izwanhadi@petronas.com.my











All information is provided in this letter is accurate, to the best of our knowledge, as of the date this letter was issued.